



Simco
We've Got You Covered

*211 Gunther Ln.
Belle Chasse, LA 70037
Tel: 504.393.9455*

VERSAKOTE-2002

Description: An all purpose one component, high solids, low VOC maintenance coating specially suitable for application to surfaces with minimum of surface preparation. Provides exceptional protection of steel exposed to brine, salt air, water and industrial atmosphere e.g. on tanks, tank roofs, bridges and steel structures, etc.

Principle Features:

- Self-priming, surface tolerant, can be applied in a single high build coat.
- Excellent corrosion and water resistance.
- Can be easily applied over clean tight rust surfaces.
- Lead and Chromate free.

Technical Data

Generic Type:	C.S. based Polymer
Color & Finish:	Silver, Gray; Matte
Solids by Volume:	67%
Weight per Gallon	10.0 lbs. min.
Flash Point:	105°F
Theoretical Coverage:	Approx. 125 sq. ft./gallon @ 8.0 mil.
Recommended DFT	8.00 mils.
VOC:	2.2 lbs/gallon
Drying Time Hours (3-4 Mils DFT):	
To touch:	4 hours max
Tack free:	10 hours max
Dry Film:	48 hours max
Shelf Life:	1 year
Cleaner:	Mineral spirits
Number of Coats:	One, normally

Surface Preparation:

Versakote-2002 requires a minimum of surface preparation, but loose mill scale, loose rust, peeling paint and other surface contaminants such as oil; grease and water must be removed before application of coating. Water blasting, sand sweeping, power tool cleaning are economical methods of removing surface contaminants.

Mixing:

Normally none required, however, if the Versakote-2002 has been in transit or stored over an extended period of time, agitation with a "Jiffy Mixer" will restore the product if separation has occurred.

Method of Application:

The coating can be applied by brush, roller, conventional or airless spray equipment.

Ventilation:

In confined areas, provide adequate fresh air ventilation; use fresh air masks and explosion proof equipment. Forbid all flames, smoking and welding in work area. This product cures by solvent evaporation and therefore requires adequate ventilation until cured to insure against the formation of an explosive atmosphere in tanks or compartments.

WARNING!:

This product contains flammable solvents. Avoid breathing of just and vapors. Keep away from heat or open flame. Avoid contact with skin, flush with plenty of water in case of contact with skin and for eyes flush with plenty of water for 10-15 minutes. Get medical attention.

Non-Warranty:

The technical data listed herein has been compiled for your convenience and guidance, and is based upon our experience and knowledge. However, since we have no control over the use of this information of this product, no warranty expressed or implied, is intended or given. Simco Coatings, Inc. assumes no responsibility whatsoever for coverage, performance, or any other damages, including injuries resulting from use of this information or of products recommended herein.

Copyright © 2001-2004 Simco Coatings Inc. All rights reserved.