



Simco
We've Got You Covered

*211 Gunther Ln.
Belle Chasse, LA 70037
Tel: 504.393.9455*

SAFE GUARD-660 **NON-SKID COATING**

Description: A non-slip deck coating formulated on a base of chemical resistant chlorinated rubber and an abrasive, resistant to many chemicals, oils, greases, brake fluids and fresh water. It is self priming and is ideal as a non-slip coating applied over inorganic and organic Zinc rich coatings.

Recommended Uses: Suitable for all weather deck areas of ships, barges, drilling platform decks, heliports, catwalks, stairs and wherever it is important to minimize slipping hazards.

Technical Data

Color:	Yellow, gray, deck red, off-white
Finish:	Eggshell finish
Percent Volume by Solids:	38.0 ± 1.0%
Theoretical Coverage:	Approx. 600 sq. ft. / Gal. @ 1.0 mil
Flash Point:	Over 80° F
Recommended DFT:	
Wet:	7-8 mils
Dry:	2.5 - 3.0 mils
Drying Time:	
Set to touch:	1-2 hours
Recoat Time:	4-6 hours
Light Traffic:	24 hours
Heavy Traffic:	48 hours
Shelf Life:	12 months
Pot Life:	Indefinite
Packaging & Shipping Weight:	60 lbs./5 gal. 12 lbs./1 gal.
Recommended Thinner:	T-1 @ 10% if needed.

Surface Preparation:

Make sure surface is free from oil, grease, dirt or loose paint or any other surface contaminants.

Application Data:

May be applied by brush or roller. Brush on surface in a uniform coat and avoid excessive brushing to prevent "piling up". Use a rug type or short nap roller for roller application.

Warning:

Solvents in this coating are volatile and flammable. Keep containers closed and away from heat, open flames and sparks.

Non-Warranty:

The technical data listed herein has been compiled for your convenience and guidance, and is based upon our experience and knowledge. However, since we have no control over the use of this information of this product, no warranty expressed or implied, is intended or given. Simco Coatings, Inc. assumes no responsibility whatsoever for coverage, performance, or any other damages, including injuries resulting from use of this information or of products recommended herein.